AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A method for producing a magnetic recording medium having a nonmagnetic substrate coated with a magnetic coating material containing a ferromagnetic powder and a binder, comprising-wherein:

<u>preparing</u> the magnetic coating material contains a liquid A constituted by the <u>a</u> ferromagnetic powder and a solvent, and;

preparing a solution B of the a binder; and

mixing the liquid A and the solution B are mixed-together by applying an ultrasonic wave thereto, and are thereafter subjected subjecting the mixture to dispersion processing to obtain a magnetic coating material; and

coating a nonmagnetic substrate with the magnetic coating material.

- 2. (original): The method as defined in claim 1, wherein the ultrasonic wave is applied within one second after the liquid A and the solution B are mixed together.
- 3. (original): The method as defined in claim 1, wherein the liquid A is subjected to dispersion processing by applying the ultrasonic wave thereto before the liquid A and the solution B are mixed together.

AMENDMENT UNDER 37 C.F.R. § 1.111 U.S. Application No. 10/601,593

- 4. (original): The method as defined in claim 1, wherein the ferromagnetic powder is a needle particle with a major axis length of 10 to 100 nm.
- 5. (original): The method as defined in claim 1, wherein the ferromagnetic powder is a plate particle with a plate diameter of 10 to 50 nm.
- 6. (currently amended): A method for producing a magnetic recording medium having a nonmagnetic substrate coated with a magnetic coating material containing a ferromagnetic powder and a binder, whereincomprising:

<u>preparing the magnetic coating material contains</u> a liquid A constituted by the <u>a</u> ferromagnetic powder and a solvent, and;

<u>preparing</u> a solution B of the <u>a</u> binder; and

<u>subjecting</u> the liquid A is subjected to dispersion processing by applying an ultrasonic wave thereto, and thereafter <u>mixing</u> the liquid A and the solution B are mixed together <u>to obtain a magnetic coating material; and</u>

coating a non-magnetic substrate with the magnetic coating material.

- 7. (original): The method as defined in claim 6, wherein the ferromagnetic powder is a needle particle with a major axis length of 10 to 100 nm.
- 8. . (original): The method as defined in claim 6, wherein the ferromagnetic powder is a plate particle with a plate diameter of 10 to 50 nm.